


Anwendung



Werkstoff

Al-Knetlegierung
Al-Integralbau



d1 [mm]	z	v _r [m/min]	f _s [mm]	a _p [mm]	a _e [mm]	n [min ⁻¹]	v _r [mm/min]	Q [cm ³ /min]
6.00	3	650	0.060	9.000	2.400	34485	6205	134.1
8.00	3	650	0.075	12.000	3.200	25865	5820	223.5
10.00	3	650	0.090	15.000	4.000	20690	5585	335.2
12.00	3	650	0.110	18.000	4.800	17240	5690	491.6
16.00	3	650	0.120	24.000	6.400	12930	4655	715.1
20.00	3	650	0.140	30.000	8.000	10345	4345	1042.8

Reinkupfer



6.00	3	500	0.050	9.000	2.400	26525	3980	85.9
8.00	3	500	0.060	12.000	3.200	19895	3580	137.5
10.00	3	500	0.070	15.000	4.000	15915	3340	200.5
12.00	3	500	0.090	18.000	4.800	13265	3580	309.4
16.00	3	500	0.095	24.000	6.400	9945	2835	435.4
20.00	3	500	0.110	30.000	8.000	7960	2625	630.3

Thermoplaste




6.00	3	792	0.060	9.000	2.400	42015	7565	163.4
8.00	3	1056	0.075	12.000	3.200	42015	9455	363.0
10.00	3	1200	0.090	15.000	4.000	38195	10315	618.8
12.00	3	1200	0.110	18.000	4.800	31830	10505	907.6
16.00	3	1200	0.120	24.000	6.400	23875	8595	1320.1
20.00	3	1200	0.140	30.000	8.000	19100	8020	1925.1

Al-Gusslegierung



6.00	3	520	0.060	9.000	2.400	27585	4965	107.3
8.00	3	520	0.075	12.000	3.200	20690	4655	178.8
10.00	3	520	0.090	15.000	4.000	16550	4470	268.1
12.00	3	520	0.110	18.000	4.800	13795	4550	393.3
16.00	3	520	0.120	24.000	6.400	10345	3725	572.0
20.00	3	520	0.140	30.000	8.000	8275	3475	834.2



Al-Knetlegierung
Al-Integralbau



6.00	3	550	0.040	3.000	6.000	29180	3500	63.0
8.00	3	550	0.050	4.000	8.000	21885	3285	105.0
10.00	3	550	0.065	5.000	10.000	17505	3415	170.7
12.00	3	550	0.075	6.000	12.000	14590	3285	236.3
16.00	3	550	0.085	8.000	16.000	10940	2790	357.1
20.00	3	550	0.095	10.000	20.000	8755	2495	499.0

Reinkupfer



6.00	3	450	0.035	3.000	6.000	23875	2505	45.1
8.00	3	450	0.040	4.000	8.000	17905	2150	68.8
10.00	3	450	0.050	5.000	10.000	14325	2150	107.4
12.00	3	450	0.060	6.000	12.000	11935	2150	154.7
16.00	3	450	0.065	8.000	16.000	8950	1745	223.5
20.00	3	450	0.075	10.000	20.000	7160	1610	322.3

Thermoplaste



6.00	3	792	0.040	3.000	6.000	42015	5040	90.8
8.00	3	1000	0.050	4.000	8.000	39790	5970	191.0
10.00	3	1000	0.065	5.000	10.000	31830	6205	310.4
12.00	3	1000	0.075	6.000	12.000	26525	5970	429.7
16.00	3	1000	0.085	8.000	16.000	19895	5075	649.4
20.00	3	1000	0.095	10.000	20.000	15915	4535	907.2

Al-Gusslegierung



6.00	3	440	0.040	3.000	6.000	23345	2800	50.4
8.00	3	440	0.050	4.000	8.000	17505	2625	84.0
10.00	3	440	0.065	5.000	10.000	14005	2730	136.6
12.00	3	440	0.075	6.000	12.000	11670	2625	189.1
16.00	3	440	0.085	8.000	16.000	8755	2230	285.7
20.00	3	440	0.095	10.000	20.000	7005	1995	399.2